

TYPE OF FILM 膠膜種類	POLYURETHANE 聚氨基酯											
	WH6136	WH8301	WH8397	WH1040	WH1041	WH1045	WH1046	WH6500	UH6511	WH6130	WH6130NF	WH7501
適用接著之基材 BONDING FABRIC												
尼龍布Nylon Textile	★	◎	◎	◎	◎	◎	◎	★	★	★	★	★
聚酯布Polyester Textile	★	★	★	★	★	★	★★	★	★	★	★	★
醋酸纖維布Acetate Textile	★	◎	◎	◎	◎	◎	◎	★	★	★	★	★
丙烯酸布Acrylic Textile	★	◎	◎	◎	◎	◎	◎	★	★	★	★	★
棉布Cotton	★	★	★	★	★	★	★	★	★	★	★	★
羊毛Wool	★	★	★	★	★	★	★	★	★	★	★	★
苯乙烯-丁二烯-丙烯晴共聚物ABS	★	★	★	★	★	★	★	★	★	★	★	★
聚碳酸酯P.C	★	★	★	★	★	★	★	★	★	★	★	★
聚乙烯、聚丙烯PE、PP												
聚氨酯PU	★	★	★	★	★	★	★	★	★	★	★	★
聚氯乙烯 PVC	★	★	★	★	★	★	★	★	★	★	★	★
聚苯乙烯PS	◎			◎	◎	◎	◎	◎	◎	◎	◎	◎
鋁、鋼Aluminum, Steel				◎	◎	◎	◎					
玻璃Glass								★		★	★	
玻纖、碳纖Fiber glass、Carbon	◎	◎	◎	◎	◎	◎	◎	★	★	★	★	★
皮革Leather	◎	◎	◎	◎	◎	◎	◎	★	★	★	★	★
紙、木材Paper、Wood	★	★	★	★	★	★	★	★	★	★	★	★
尼龍/撥水布Nylon DWR					★一般撥	★一般撥		★一般撥		★★★★	★★★★	
特多隆/撥水布Polyester DWR					★一般撥	★一般撥		★一般撥		★★★★	★★★★	
接著加工溫度(Bonding Temp)°C	100~130	120~140	120~140	110~140	110~140	120~150	120~150	110~150	100~130	90~110	90~110	90~110
結晶速度(crystallization rate)	快 Fast	中 Mid	快 Fast	中 Mid	中 Mid	中 Mid	中 Mid	中 Mid	中 Mid	慢 Slow	慢 Slow	中 Mid
厚度Thickness : (mm)	0.03-0.30	0.05-0.30	0.05-0.10	0.05-0.30	0.05-0.30	0.05-0.30	0.05-0.30	0.05-0.30	0.03-0.30	0.05-0.30	0.05-0.30	0.05-0.30
每捲標準長度Length : (YD)	100	100	100	100	100	100	100	100	100	100	100	100
標準寬度 Width :(inch)	48-58	48-58	48-58	48-58	48-58	48-58	48-58	46-58	48-58	48-56	48-56	48-58
手感	硬Hard	柔軟Soft	硬Hard	柔軟Soft	柔軟Soft	柔軟Soft	柔軟Soft	柔軟Soft	柔軟Soft	柔軟Soft	柔軟Soft	柔軟Soft
耐水洗溫度°C	45	60	45	45	★60	★60	60	60	60	★60	★60	60
乾洗 Dry Wash	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK
襯底基材 (Release Paper)				離型紙/PE膜	離型紙/PE膜	離型紙/PE膜	離型紙/PE膜	離型紙/PE膜	離型紙/PE膜	離型紙	離型紙	離型紙/PE膜

★：優質 EXCELLENT (重疊式黏合強度為7kg/mm以上,對貼式黏合強度0.82kg/mm以上)

◎：良好 GOOD (重疊式黏合強度為5.4kg/mm~7kg/mm,對貼式黏合強度0.63kg/mm~0.82kg/mm)